

ADVANCE PRODUCTS & SYSTEMS, INC.

DuoCon Centralizers

Corrosion Resistant Polyethylene

DuoCon Centralizers are used to support and space a section of pipe inside a secondary pipe on dual containment systems. These plastic centralizers can be used on all types of pipe including fiberglass, PVC, polyethylene and steel.

APS centralizers are manufactured from injection molded, high density polyethylene. Commonly called spacers or spiders, DuoCon Centralizers are lightweight, economical, and easy to install, requiring only a screwdriver. We recommend installation every 8 to 12 feet.

Other benefits of polyethylene include high impact strength and abrasion resistance. The low friction of polyethylene facilitates easy installation when sliding the central pipe.

Molded into the inner surface are grooves which prevent slippage and cold flow of coated pipe.


pipe.
The APS DuoCon Centralizer has excellent dielectric resistance and low moisture absorption which allows it to be used as an insulator for


Sizes are available from 2" to 12" with a standard runner height of 1".

cathodic protection.

Extensions of as much as 4" can be added optionally.

Centralizers 14" and above are available in multi-segments.





SPECIFICATIONS

SIZE (Nominal	RUN NER	NUMBER	WEIGH	UNIT S DED
1 X 3	1/2"	2	.08	200
1 1/2 X 3	1/2"	2	.12	200
2 X 4 / 2 X 6	5/8"	2	.52	200
3 X 6 / 3 X 8	3/4"	2	.67	130
4 X 6	9/16"	2	.80	180
4 X 8	1″	2	1.03	100
4 X 10	1 1/2"	2	1.25	80
4 X 12	2″	2	1.25	70
6 X 10	1″	2	1.70	70
6 X 12	1 1/2"	2	1.94	50
6 X 14	2″	2	2.00	35
8 X 12	1″	2	2.25	40
8 X 14	1 1/2"	2	2.50	25
8 X 16	2″	2	2.63	20
10 X 14	1"	2	2.40	30
10 X 16	1 1/2"	2	2.63	20
10 X 18	2"	2	2.75	15
12 X 16	1″	2	2.75	25
12 X 18	1 1/2"	2	2.88	20
12 X 20	2"	2	3.00	15

- Centralizers 14" and above available upon request
- Additional runner height up to 4" optional
- Stainless steel hardware available upon request

PHYSICAL PROPERTIES

Dielectric Strength

450-500 Volts/Mil

Compressive Strength

3200 psi

Flexural Yield Strength

1000 psi

 Maximum Continuous Operating Temperature

221°F (105°C)

Tensile Strength

3100 - 5500 psi

Impact Strength

2.0 ft-lbs/in. of notch

Water Absorption

< 0.01%

ORDERING INSTRUCTIONS

Please Specify the Following:

- Quantity
- Pipe O.D.
- Type of Pipe
- Secondary Pipe O.D.
- Secondary Pipe Wall Thickness
- · Height of Runners





ADVANCE PRODUCTS & SYSTEMS, INC.

-3860

********		_
		Ē
		_

	Distributed By:
1	